

UPM Raflatac Technical Information

13-03-2022 EN SI

Product	PP WHITE TC 60 / RP37 / KRAFT SPECIAL 85
Sales Code	5N/RP37/91
EAN	6415788047392
Product use	Biaxially oriented, white, cavitated and top coated PP film with pearlescent shade; giving excellent print surface to most of the printing methods. Low density of the film offers tool for economical multipurpose labelling. Combined with permanent RP37 and Kraft backing for applications which require better layflatness properties than a glassine backing might offer.

Typical technical values

Face PP WHITE TC 60

Product	A white, glossy, biaxially oriented, cavitated, top-coated polypropylene film.		
Substance	46	g/m ²	DIN 53352
Caliper	61	µm	DIN 53370
Opacity	88	%	DIN 53146/1
Printability	Suitable for flexography, screen and offset printing methods, as well as UV inkjet and Xeikon digital label presses. Thermal transfer is possible with selected wax-resin and resin ribbons.		

Adhesive RP37

Type	Permanent		
Composition	Waterborne acrylic		
Tack	10	N/25mm	FTM 9

Backing KRAFT SPECIAL 85

Product	A white wood-free kraft backing paper.		
Substance	87	g/m ²	ISO 536
Caliper	82	µm	ISO 534
Tensile strength MD	8,7	kN/m	ISO 1924
Tensile strength CD	3,8	kN/m	ISO 1924

Performance

Total caliper	161 µm
Minimum labelling temperature	5 °C
Service temperature	-20 °C to 80 °C
Shelf life	From date of manufacture: 24 months, under FINAT defined storage conditions (+20-25°C and RH 40-50%). Prolonged storage at higher temperatures and/or humidity levels will shorten the shelf life.

Information

Limitations	There is a risk that static electricity will impede conversion if the product is sheeted, and the Kraft liner does not guarantee layflat properties in this product construction.
-------------	---

Disclaimer

The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.

