

Technical Data Sheet

updated
checked

29.06.2023
30.10.2023

Product Jetflag K

6144K

Material 100 % Polyester

Stock widths app. 260 cm, 320 cm

Making-up rolled on paper cores

Packaging Wrapped with foil (LDPE)

Ecology according to STANDARD 100 by OEKO-TEX,
product class 2
(direct contact with skin)

Ink-type transfer printing,
direct printing with dye-sub inks

Weight

acc. to DIN EN 12127	110.00	[g/m ²]	+ - 3	[%]
----------------------	--------	---------------------	-------	-----

Shrinkage

Heat Shrinkage, 195 °C, 90 sec,
lengthwise

acc. to PA13	-2.50	[%]	+ - 1	[%]
--------------	-------	-----	-------	-----

Heat Shrinkage, 195 °C, 90 sec,
crosswise

acc. to PA13	-1.00	[%]	+ - 1	[%]
--------------	-------	-----	-------	-----

Tearing strength

Elongation at 100 N, longitudinal direction

acc. to DIN EN ISO 13934-1	6.00	[%]	+ - 20	[%]
----------------------------	------	-----	--------	-----

Elongation at 100 N, cross direction

acc. to DIN EN ISO 13934-1	20.00	[%]	+ - 20	[%]
----------------------------	-------	-----	--------	-----

Maximum tensile elongation, longitudinal
direction

acc. to DIN EN ISO 13934-1	37.00	[%]	+ - 20	[%]
----------------------------	-------	-----	--------	-----

Maximum tensile elongation, cross direction

acc. to DIN EN ISO 13934-1

65.00 [%]

+ - 20 [%]

Maximum tearing strength, longitudinal direction (min.)

acc. to DIN EN ISO 13934-1

min. 310.00 [N/5 cm]

[N/5 cm]

Maximum tearing strength, cross direction (min.)

acc. to DIN EN ISO 13934-1

min. 530.00 [N/5 cm]

[N/5 cm]

We do not accept liability for errors. The confirmed properties are valid in the state of delivery. Any further processing can change them (e.g. washing / flame retardancy).

Please pay attention to our general considerations regarding fabrication at www.g-o-friedrich.com

Printing mistakes and changes are reserved.