INRICHTING ERKEND BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Texo Trade Services B.V.
Dhr. Simon Supusepa
Oostbaan 601
2841 ML MOORDRECHT
Nederland

Your notice of	**Your reference**	**Date**
11-02-2020		20-03-2020

Analysis Report 20.00808.01

Required tests :
EN ISO 11925-2 (2010) **Reaction to fire tests – Ignitability of building products subjected to direct impingement of flame - Single-flame source test**

Identification number	Information given by the client	Date of receipt
T2002999	F950FR02 Blackback Soft	11-02-2020
T2003000	F926FR02 Basic Display 210	11-02-2020
T2003001	F935FR02 Display Stretch 240	11-02-2020

Kristina De Temmerman
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

INRICHTING ERKEND BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Reference: **T2002999 - F950FR02 Blackback Soft**

Reaction to fire tests – Ignitability of building products subjected to direct impingement of flame - Single-flame source test

Date of ending the test	19-03-2020
Standard used	EN ISO 11925-2 (2010)
Product standard	EN 13501-1 (2019)

Construction materials

Deviation from the standard	-
Conditioning	23°C, relative humidity 50% Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Specimens have not been cleaned

Flame application time (s)	30
Flame application	Surface - front

	Length			Width		
	1	2	3	4	5	6
Time to reach 150 mm mark (s)	*	*	*	*	*	*
Ignition filter paper within 60 s after flame application	no	no	no	no	no	no

* = time to reach the mark > 60 s or mark not reached

RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Reference: **T2002999 - F950FR02 Blackback Soft**

Reaction to fire tests – Ignitability of building products subjected to direct impingement of flame - Single-flame source test

Date of ending the test	19-03-2020
Standard used	EN ISO 11925-2 (2010)
Product standard	EN 13501-1 (2019)

Construction materials

Deviation from the standard	-
Conditioning	23°C, relative humidity 50% Minimum 14 days or until constant mass is achieved